



BLACK GROUNDCOVER

| MECHANICAL PROPERTY | TEST METHOD | UNIT | TYPICAL AVERAGE ROLL VALUE | |
|--------------------------|----------------|---------------------|----------------------------|----|
| | | | MD | CD |
| Grab Tensile Strength | ASTM D -4632 | lbs | 170 | 80 |
| Grab Tensile Elongation | ASTM D-4632 | % | 22 | 15 |
| Trapezoid Tear Strength | ASTM D-4533 | LBS | 70 | 50 |
| Puncture | ASTM D-4833 | LBS | 75 | |
| Water Flow | ASTM D-4491 | Gal/min/ft2 | 10 | |
| Mullen Burst Strength | ASTM D-3786 | Psi | 290 | |
| UV Resistance @ 1200 hrs | ASTM G 154 QUV | % strength retained | 70 | |

| PHYSICAL PROPERTIES | TEST METHOD | UNIT | TYPICAL VALUE |
|---------------------|-------------|--------|---------------|
| Weight | ASTM D 5261 | Oz/yd2 | 3.2 |
| Fiber Content | | | 100% PP |

