



BLACK GROUNDCOVER

MECHANICAL PROPERTY	TEST METHOD	UNIT	TYPICAL AVERAGE ROLL VALUE	
			MD	CD
Grab Tensile Strength	ASTM D -4632	lbs	170	80
Grab Tensile Elongation	ASTM D-4632	%	22	15
Trapezoid Tear Strength	ASTM D-4533	LBS	70	50
Puncture	ASTM D-4833	LBS	75	
Water Flow	ASTM D-4491	Gal/min/ft2	10	
Mullen Burst Strength	ASTM D-3786	Psi	290	
UV Resistance @ 1200 hrs	ASTM G 154 QUV	% strength retained	70	

PHYSICAL PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUE
Weight	ASTM D 5261	Oz/yd2	3.2
Fiber Content			100% PP

