



MONO-KNIT SHADE

| CONTENT | | UNITS | SOLAR SHADE MONO-KNIT | | | TEST METHOD |
|------------------|------|-----------------------|-----------------------|-------------|-------------|------------------|
| Shade factor | | % | 50% | 60% | 70% | AATCC148 |
| Weight (+/- 10%) | | gr/m2 (oz/yd2) | 170 5.0 | 210 6.2 | 240 7.1 | ISO 3801 |
| Tensile Strength | Warp | kg/5cm (lbs/2inch) | 39 86.0 | 52 114.6 | 60 132.3 | ISO 5082 Grab |
| | Weft | | 47 103.6 | 63 138.9 | 73 160.9 | |

*available in white, green, blue & others available to special order

*also available in 30% & 40% with special order